

Technical Data Sheet



e-Hardener Fast

Field of application:	Car-refinish and commercial vehicles
Chemical bases:	Non-yellowing highly durable aliphatic isocyanate resin
General qualities:	e-Hardener Fast for: use at low temperatures on small medium-sized objects and for partial and spot-repair. It should be used between 8-18 °C
Auxiliary materials:	e-Acryl/C2 MS Clear Coat, P-Acryl Solid Colour Top Coats, 3+1 HS Primer, 4+1 HS Primer, 5+1 HS Primer, e-5+1 HS Primer, T 8-18/18-25/25-35-35+ Universal Thinners.
Physical properties	
Density:	0.975-0.980 kg/L
Flash Point:	>21°C
Vol. % solids:	32
Viscosity:	55-60 sec (DIN CUP 4 mm/ 20 °C)
Gloss:	See info P-Acryl Solid Colour Top Coats, e-Acryl/C2 MS Clear Coat
Cleaning the equipment:	Universal Acrylic Thinners and Nitro Cellulose Thinners
Colour:	Clear
Storage life:	Under normal storage conditions and unopened tins for up to 1-1.5 years. If the tin is opened, it can be kept for no longer than one week. The tin should be closed immediately after use. Stable approximately one week, depending on temperatures and humidity.

For professional use only! The technical data in these publications has been carefully selected and arranged by us. It is based upon our knowledge on the subject at the date of issuance. The information is given for information only. For safety see MSDS.