

Technical Data Sheet



e-Hardener Standard

| | |
|--------------------------------|---|
| Field of application: | Car-refinish and commercial vehicles |
| Chemical bases: | Non-yellowing highly durable aliphatic isocyanate resin |
| General qualities: | e-Hardener Standard for use at normal temperatures on small medium-sized objects and for partial and spot-repair. It should be used between 18-30 °C |
| Auxiliary materials: | e-Acryl/C2 MS Clear Coat, P-Acryl Solid Colour Top Coats, 3+1 HS Primer, 4+1 HS Primer, 5+1 HS Primer, e-5+1 HS Primer, T 8-18/18-25/25-35/35+ Universal Thinners. |
| Physical properties | |
| Density: | 0.975-0.980 kg/L |
| Flash Point: | >21 °C |
| Vol. % solids: | 33 |
| Viscosity: | 55-60 sec (DIN CUP 4 mm/ 20 °C) |
| Gloss: | See info P-Acryl Solid Colour Top Coats, e-Acryl/C2 MS Clear Coat |
| Cleaning the equipment: | Universal Acrylic Thinners and Nitro Cellulose Thinners |
| Colour: | Clear |
| Storage life: | Under normal storage conditions and unopened tins for up to 1-1.5 years. If the tin is opened, it can be kept for no longer than one week. The tin should be closed immediately after use. Stable approximately one week, depending on temperatures and humidity. |

For professional use only! The technical data in these publications has been carefully selected and arranged by us. It is based upon our knowledge on the subject at the date of issuance. The data is given for information only. For safety see MSDS.